

BBC-1000

Mono Hot Fill



Proprietary blend of hot-fill-rated polyolefins. Suitable for hot fill applications of 180 – 195°F filling, chill and reheat to 212°F boiling when lock seal is made between film plies.

Typical Film Property	ASTM	Physical Properties
Thickness		.002 - .006
Peak Tensile (psi)	D-882	MD – 3,800 TD – 3,800
Peak Elongation (%)	D-882	MD – 600 TD – 650
Lock Seal (°F)	MAGMA	≥ 260

NOTE: The data presented above is for the product type described and is based on random tests that are not statistically valid. The values should only be used for reference and are not to be used for any type of specification. Novolex does not monitor these values or manufacture to these values. Please be advised that values are known to change based on normal manufacturing variables such as production line, and lot to lot variations of raw materials. There is no guaranty expressed or implied regarding the use of this information or its suitability for a particular application.